

ZINCOSIL 430

COLD GALVANIZATION ZINC SPRAY- SHINING



Characteristics

Appearance:	Pure zinc 98% in synthetic vehicle (resins)
Pigment Purity:	> 98%
Colour:	light grey. Shining.
Propellant:	Denatured and odourless hydrocarbon.
Dry film Thickness:	20-40 µm micron (cross coating)
Covering Power:	High
Covering value:	About 120ml/m ² (cross coating)
Dry time:	5-10 minutes. (Fast Drying- It does not drip)
Electric conductivity:	High
Abrasion Resistance:	Very High
Cross cutting:	(DIN 53151 - ISO 2409) = GT0/GT1
Oxidation resistance:	Very Good resistance to corrosion
Temperature resistance:	From -50°C to + 300°C
CFC free	

Properties:

- It does not contain chlorinated solvents
- High zinc content
- Fast drying
- It doesn't drip
- High covering power; It permits over painting
- High resistance to corrosion
- Good resistance to atmospheric agents, washing, oxidation of salty fog
- Colour similar to a galvanising
- Long lasting protection

Description

ZINCOSIL 430 is used for cold galvanization of all metals. Zinc spray with high zinc content is particularly suitable for retouches in soldering, to restore or galvanize metal sheets, to galvanize and protect weather-exposed bolts for long periods, to restore the zinc film on gates, doors, metal sheets, tanks and metal structure. The Aerosol is endowed with a no-drop nozzle and it permits to use it without staining. ZINCOSIL 430 is also a good protective against corrosion of atmospheric agents, saltiness, and humidity

Instructions of use

Shake the can before use at least for one minute until the little ball inside the can is free to move. During the application shake the product in order to keep it homogeneous. Clean and degrease the parts to treat. Spray at 25 cm distance. After the use overturn the aerosol and spray the product for few seconds to dodge the obstruction of the valve.

Packaging

Spray Aerosol ml 400
Box 12 Aerosol
Product Code 14511/04

Head office and Production

Siliconi Commerciale® SpA
Via Francia 4
36053 Gambellara
Vicenza – ITALY
phone + 39.0444.649766
fax +39.0444.440018
e. mail: info@siliconi.it
www.siliconi.it

Production since 1957

The information and recommendations contained in this document is offered in good faith based on our current knowledge and belief accurate at the date of publication. Nothing herein is to be considered as a warranty, express or otherwise. In all cases, it is the responsibility of the user to determine the applicability of such information or the suitability of any products for their own particular purpose with local legislation and for obtaining the necessary certifications and authorisations. Siliconi Commerciale's sole warranty is that the products will meet its sales specification. The manufacturer cannot be held responsible in case of damages caused by incorrect use of the product.
® indicates a Registered TradeMarks of Siliconi Commerciale. All Rights Reserved.